



Sea~Barrier[®] 3000

Ablative Antifouling

Data Sheet

FEATURES

Advantages:

- High performance TBT-free (Tri-Butyl Tin-free) antifouling – contains high levels of cuprous oxide
- Self polishing/ablative mechanism inhibits the attachment of fouling organisms
- Excellent static exposure performance
- Controls common types of fouling for periods up to 36 months, depending on sailing pattern and applied system
- Increased periods between dry dockings leading to a reduction in operating costs
- Case histories to 5 years protection

Approvals

NZ HSNO Act – Reg. No. HSR000035.

APVMA Approval Number: 64133

Meets IMO 2003 Tin-Free Regulations; MEPC.102(48) – Independently tested and certified by PRA reference; 07/269/NP-C .

Bureau Veritas IMO Type Test Approval Certificate No. 20612/BO BV.

Lloyds Register – Recognised TBT Free Certificate No. MNDE/2012/4953 (for New Zealand manufacture).

Lloyds Register – Recognised TBT Free Certificate No. MNDE/2012/4957 (for Australia manufacture).

Limitations of Use:

- **Not suitable for aluminium vessels or stern drives**

RECOMMENDED USES

Sea~Barrier[®] 3000 is a high performance, ablative antifouling coating.

Sea~Barrier[®] 3000 is recommended for use where:

- Regulations ban the use of organo-tin based products
- Superior ablative properties are required
- Long term, well proven protection is desired

Sea~Barrier[®] 3000 is the ideal antifoul coating for:

- Maintenance Docking
- New Building

Sea~Barrier[®] 3000 is suitable for:

- Barges
- Tug Boats
- Ferries
- Charter Vessels
- Yachts
- Fishing Vessels
- Numerous other sea going vessels

SPECIFICATION DATA

Coating Type: Ablative Matrix
Colour: NZ & Aust. Copper Black, Deep Red, Ocean Blue
Packaging: NZ & Aust: 4 and 10 litres Single component
Flash Point: 37°C Setaflash
Mix Ratio: N/A – single component
Pot Life: N/A
Thinner: Do NOT thin unless absolutely necessary
Clean Up: Altex Thinner #12
Shelf Life: 12 months minimum
Storage: Store under cool dry conditions

Density: 1.84 kg per litre
VOC: 414g per litre
Volume Solids: 52%
Theoretical Coverage Rate:
 5.2 sq. metres per litre at 100 microns dry
 6.9 sq. metres per litre at 75 microns dry
Recommended Film Thickness Per Coat:
 192 microns wet to obtain 100 microns dry
 144 microns wet to obtain 75 microns dry
Application: Spray, Brush or Roller
Recommended Dry Times (100µm DFT / 25°C / 50% RH):
Dry to Recoat:
 Minimum 6 hours
 Maximum Not critical
Dry to Launch:
 Minimum 8 hours
 Maximum Indefinite

SURFACE PREPARATION

All surfaces must be sound and free of oil, grease, dirt, loose and flaking paint, moisture and other foreign substances prior to application of Sea-Barrier® 3000 Anti-Fouling.

Sea-Barrier® 3000 Anti-Fouling is designed to be applied over Altex Coatings epoxy bottom systems. It is also compatible with a wide range of anti-corrosive and anti-fouling coatings.

Sea-Barrier® 3000 Anti-Fouling must be applied over the epoxy bottom coatings before they have cured hard. Apply Sea-Barrier® 3000 Anti-Fouling when the epoxy is tack free but still soft to finger pressure. If the epoxy has cured too hard, apply another thin coat of epoxy before applying Sea-Barrier® 3000 Anti-Fouling.

SeaBarrier® 3000 may be applied over single pack primers such as Multi-bond Primer, and Chem-Bar™ 3500.

Refer to relevant product data sheet for further information.

Sea-Barrier 3000® Anti-Fouling can also be applied over a wide range of existing anti-fouling coatings, including most cuprous oxide containing, copolymer types. Existing anti-fouling must be secure and intact, and must be water blasted clean before applying Sea-Barrier® 3000 Anti-Fouling.

Consult your Altex Coatings Representative for specific recommendations regarding compatibility with existing anti-fouling systems. Existing anti-fouling must be secure and intact. Refer to Repainting below for surface preparation directions.

Repainting: High pressure water clean (5,000 – 10,000 psi/330 – 660 bar) to remove all marine growth, hydrolysed antifouling, salts, loose paint and any other foreign matter.

The cleaned surface, once dry should be free of any powdered antifouling residues and should be inspected for defects in the film. Repairs to the coating system should be completed before the application of any subsequent coat of antifouling.

DIRECTIONS FOR USE

Mixing:

Before use Sea-Barrier® 3000 Anti-Fouling must be thoroughly stirred, preferably with an air-powered mixer, to ensure a homogenous condition without any settlement remaining on the bottom of the container.

Thinning:

Sea-Barrier® 3000 anti-fouling does not require any thinning, except possibly in hot windy conditions. Sea-Barrier® 3000 Anti-Fouling is thinned using Altex Thinner #12, additional coats may be required to attain the correct film thickness.

Application:

Sea-Barrier® 3000 Anti-Fouling can be applied by either conventional spray or airless spray equipment.

Suggested spray equipment:

Conventional Air Spray

1.4mm to 2.2mm Fluid tip with appropriate air cap.

Airless Spray

Pump Ratio	30:1
Material Hose	3/8" I.D min
Tip Size	0.015 – 0.021

(Note: The above is a guide. Other equipment to the above may be used.)

Important:

Whilst Sea-Barrier® 3000 Antifouling can be applied by spray, brush or roller, it is strongly recommended that heavy-duty airless spray equipment be used to ensure the specified film thickness per coat is applied. Film thickness control is critical to the performance of the coating, as service life is a direct function of film thickness. Additional coats may be required to attain the correct film thickness if the coating is applied by brush or roller.

Clean-up:

Use Altex Thinner #12.

PRECAUTIONS

For industrial use only: Read and follow all the caution statements on this Product Data Sheet, the product label and the Safety Data Sheet (SDS) for health and safety information prior to use.

Sea-Barrier® 3000 is flammable. Keep away from heat, sparks and open flame. Use with adequate ventilation. May cause eye and skin irritation. Do not breathe vapour or spray. Wear suitable protective clothing such as gloves and eye and face protection.

ALTEX COATINGS LIMITED

Head Office
New Zealand
91 - 111 Oropi Road
Greerton, Tauranga
PO Box 142
Tauranga Mail Centre

Phone: +64 7 5411 221
Fax: +64 7 5411 310

www.altexcoatings.com

Head Office
Australia
7 Production Avenue
Molendinar
Queensland 4214
Australia

Phone: +61 7 5512 6600
Fax: +61 7 5512 6697

www.altexcoatings.com

DISCLAIMER

This is not a specification and all of the information is given in good faith. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated, the manner of use and whether there is any infringement of patents is the sole responsibility of the user. The manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. For application in special conditions, consult the manufacturer for detailed recommendations.

It is the users' responsibility to ensure they have the latest product data sheet and Safety Data Sheet. Check the data sheet date with the listings at www.altexcoatings.com.