

Technical Datasheet



MAXGUARD™ MP Premium Marine Series Gelcoat

MAXGUARD™ MP (Marine Performance) Series gelcoats are formulated to beat the elements and protect your watercraft from sun, saltwater and rough handling for lasting exterior beauty. MAXGUARD™ MP gelcoats are engineered to spray well in the fabrication process particularly where tapelines are critical and have been proven over the years to perform in conditions requiring high levels of protection against damaging UV light, excellent blister resistance, or where excessive ambient temperatures exist.

- Excellent weathering and blister resistance.
- Exceptionally application friendly.
- Outstanding tape line pulls.

Typical Properties¹ at 25°C (77°F)

| | Whites | Colors |
|--|------------|------------|
| Viscosity, Brookfield RVT#4 @20 rpm | 3500 cps | 3800 cps |
| Thix Index, Brookfield RVT 5/50 rpm | 6 | 6.5 |
| Gel Time (1.8% MEKP-9) ⁽²⁾ | 18 minutes | 18 minutes |
| HDT 2% MEKP M-50 Post Cure: 24 HRS at 50 °C ⁽³⁾ | 71 | °C |

¹Properties are typical values based on material tested in our laboratories. Typical values should not be construed as a guaranteed analysis of any specific lot or as specification items.

²Registered trademark of Arkema, Inc. ⁽³⁾ MEKP M-50 Registered trademark of AkzoNobel, Inc.

Application and use

MAXGUARD MP gelcoats are premium gelcoats for spray applications. These gelcoats are preferred by boat shops for their superior application properties as well as their excellent weatherable and water resistant finish.



Ashland is committed to the continuous evolution of technology and service solutions that promote health, safety and environmental protection around the world.

* Registered service mark of the American Chemistry Council. © Registered trademark and ™ trademark of Ashland Inc.

Technical Datasheet



MAXGUARD™ MP Premium Marine Series Gelcoat

| | |
|----------------------------|--|
| Certificates and approvals | The manufacturing, quality control and distribution of products, by Ashland Performance Materials, are complying with one or more of the following programs or standards: Responsible Care, ISO 9001, ISO 14001 and OHSAS 18001. |
| Handling and storage | <p>DOT Label required: Flammable Liquid. This product contains ingredients which could be harmful if mishandled. Contact with skin and eyes should be avoided and necessary protective equipment and clothing should be worn.</p> <p>For good working practices, see Ashland's "Gelcoat Handling Guide". Store at temperatures between 65°F(18°C) & 80°F(27°C). Avoid exposure to heat sources such as direct sunlight or steam pipes. Agitate before use. Gelcoats perform best when temperature of the workshop, materials and tools are between 65-80°F(18-27°C) and relative humidity below 70%. A high quality MEK peroxide should be used between 1.5-2.5%. Keep sealed and avoid outdoor storage to prevent moisture pick-up and monomer loss. Rotate stock.</p> <p>Commercial Warranty: When stored in accordance with above conditions, Ashland warrants this product to remain within specifications for 3 months from date of shipment. All things being equal, higher storage temperatures reduces product stability and lower storage temperatures extends product stability.</p> |
| Notice | <p>All information presented herein is believed to be accurate and reliable, and is solely for the user's consideration, investigation and verification. The information is not to be taken as an express or implied representation or warranty for which Ashland assumes legal responsibility. Any warranties, including warranties of merchantability, fitness for use or non-infringement of intellectual property rights of third parties, are herewith expressly excluded.</p> <p>Since the user's product formulations, specific use applications and conditions of use are beyond the control of Ashland, Ashland makes no warranty or representation regarding the results which may be obtained by the user. It shall be the sole responsibility of the user to determine the suitability of any of the products mentioned for the user's specific application.</p> <p>Ashland requests that the user reads, understands and complies with the information contained herein and the current Material Safety Data Sheet.</p> |



Proudly distributed by RF Composites Pty Ltd; Australian distributor of Ashland AME resins, Maxguard & Enguard gelcoat products.



Ashland is committed to the continuous evolution of technology and service solutions that promote health, safety and environmental protection around the world.
 * Registered service mark of the American Chemistry Council. © Registered trademark and ™ trademark of Ashland Inc.