

Technical Data

HARDTOP XP



Product description

A two-pack high solid, aliphatic polyurethane topcoat with excellent gloss and colour retention. Hardtop XP bases are intermediates and need to be processed before use.

Recommended use

As a glossy topcoat over most epoxy systems where a durable, weather-resistant finish is required in a wide range of aggressive atmospheres.

Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry (μm)	40	100	60
Film thickness, wet (μm)	65	160	95
Theoretical spreading rate (m^2/l)	15,8	6,3	10,5

Physical properties

Colour According to colour card and Multicolor tinting system (MCI)
Solids (vol %)* 63 \pm 2

Flash point 30°C \pm 2 (Setaflash)

VOC 2,88 lbs/gal (345 gms/ltr) USA-EPA Method 24
320 gms/ltr UK-PG6/23(97). Appendix 3

Gloss Glossy
Gloss retention Excellent
Water resistance Very good
Abrasion resistance Very good
Solvent resistance Very good
Chemical resistance Very good
Flexibility Very good
*Measured according to ISO 3233:1998 (E)

Surface preparation

All surfaces should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

Coated surfaces

Clean, dry and undamaged compatible primer. Please contact your local Jotun office for more information.

Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

Condition during application

The temperature of the substrate should be minimum 0°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying.

Application methods

Spray	Use airless spray or conventional spray
Brush	Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.
Roller	May be used. However when using roller application care must be taken to apply sufficient material in order to achieve the specified dry film thickness.

Application data

Mixing ratio (volume)	10:1
Mixing	10 parts Comp. A (Base) to be mixed thoroughly with 1 part Comp. B (Curing agent).
Pot life (23°C)	1,5 hours
Thinner/Cleaner	Jotun Thinner No. 10
Guiding data airless spray	
Pressure at nozzle	15 MPa (150 kp/cm ² , 2100 psi)
Nozzle tip	0.28-0.38 mm (0.011-0.017")
Spray angle	40-80°
Filter	Check to ensure that filters are clean.
Note	Jotun Thinner No. 26 is supplied and used in USA due to legislation.

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- * Good ventilation (Outdoor exposure or free circulation of air)
- * Typical film thickness
- * One coat on top of inert substrate

Substrate temperature	5°C	10°C	23°C	40°C
Surface dry	16 h	6 h	3,5 h	2 h
Through dry	24 h	14 h	7 h	4 h
Cured	21 d	14 d	7 d	3 d
Dry to recoat, minimum	24 h	14 h	7 h	4 h
Dry to recoat, maximum ¹				

1. The surface should be dry and free from any contamination or chalking prior to application of the subsequent coat.
2. Early exposure to condensation (high humidity, low temperature) may cause colour and/or gloss variations.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Typical paint system

Jotacote Universal	1 x 150 µm	(Dry Film Thickness)
Hardtop XP	1 x 60 µm	(Dry Film Thickness)
Jotamastic 87	1 x 150 µm	(Dry Film Thickness)
Hardtop XP	1 x 60 µm	(Dry Film Thickness)

Other systems may be specified, depending on area of use

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing size

20 litre unit: 18,2 litres Comp. A in a 20 litre container and 1,8 litres Comp. B (curing agent) in a 3 litre container or

5 litre unit: 4,55 litres Comp. A in a 5 litre container and 0.45 litre Comp. B (curing agent) in a 1 litre container

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Head Office & Nordic

Jotun A/S
P.O. Box 2021
N-3248 Sandefjord
Norway
Phone +47 33 45 70 00
Fax +47 33 46 46 13

Europe

Jotun Paints (Europe) Ltd.
Stather Road, Flixborough
North Lincolnshire DN15
8RR
United Kingdom
Phone +44 172 44 00 000
Fax +44 172 44 00 100

Middle East

Jotun U.A.E Ltd. LLC.
Al Quoz Industrial Area
P.O Box 3671
Dubai U.A.E
Phone +971 4 3 39 50 00
Fax +971 4 3 38 06 66

South East Asia

Jotun (Singapore) Pte. Ltd.
No 11-15, Sixth Lok Yang
Road
Jurong
Singapore 628 111
Phone +65 6265 4711
Fax +65 6265 7484

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED 20 JUNE 2007 BY JOTUN
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED